

WALLTITE® Max Series Closed-cell Spray Foams

BUILDING ENVELOPE INSULATION MATERIAL

Description:

WALLTITE Max is a two-component closed-cell spray polyurethane foam system utilizing an EPA-approved, zero ozone-depleting hydrofluoroolefin (HFO) blowing agent having extremely low (less than 1) global warming potential (low-GWP). It is designed for use in residential construction and common commercial insulation applications. WALLTITE Max is compatible with most common construction materials and can only be processed with BASF Elastospray® 8000A isocyanate.

The benefits of **WALLTITE Max** include:

- Superior thermal insulation
- Control of moisture infiltration
- Air Infiltration Control
- Non-fibrous material
- Offers structural improvement
- Installation speed
- Classified as FEMA Class 5 flood damage resistant material

AVAILABLE REACTIVITIES	AMBIENT TEMPERATURE RANGE
WALLTITE Max R	40 – 120 °F
WALLTITE Max W	20 – 55 °F

Physical Properties ⁽¹⁾

PROPERTY	METHOD	WALLTITE Max
Resin		
Specific Gravity at 70°F	ASTM D1638	1.20
Viscosity at 77°F (cps)	Brookfield	600 – 800
Cured Foam		
Density, center at 2"-3" per pass (pcf)	ASTM D1622	1.8-2.0 nominal
Closed Cell Content (%)	ASTM D6226	>95
Thermal Resistance ⁽²⁾ (Aged)		
R-value (ft ² hr °F/Btu in)	ASTM C518	7.4/ inch @ < 3.5" thick
R-value (ft ² hr °F/Btu in)		7.1/ inch @ ≥ 3.5" thick
Compressive Strength (psi) ⁽³⁾	ASTM D1621	28.8
Tensile Strength (psi) ⁽³⁾	ASTM D1623	>32
Dimensional Stability (% change) 158°F / 97% RH / 168 hrs	ASTM D2126 (168 hrs)	-1.9% total change
Water Vapor Transmission	ASTM E96	1.09 Perms at 2"
Vapor Permeance	(Calculated)	<1.0 Perms @ 1.25" (Class II Vapor Retarder)
Air Leakage ⁽⁴⁾ (L/s*m ² @ 75 Pa ΔP)	ASTM E2178	Meets <0.02 @ 1.0 Inch (Air impermeable insulation)
Water Absorption (Vol %)	ASTM D2842	<1%
Surface Burning Characteristics		
Flame Spread Index	ASTM E84	≤ 25
Smoke Development Index	ASTM E84	≤ 450

⁽¹⁾ These values and physical property data are typical for SPF material applied in a development facility and from samples prepared using equipment configurations relevant to controlled laboratory conditions. Actual SPF performance and physical properties may vary with differences in application (i.e., environmental conditions, process equipment and configuration, material performance, etc.). As a result, these published properties should be used as guidelines for evaluation purposes only.

⁽²⁾ The physical property graph shows the R-value of this spray foam insulation. "R" refers to resistance to heat flow. The higher the R-value, the higher the insulating power. See the installation card and the fact sheet on R-values.

⁽³⁾ Minimum value necessary to meet ASTM C1029 Type II standard is > 25 for compressive and > 32 for tensile strength. ⁽⁴⁾ Using a conversion factor of 1 L/s* m² = 0.196850394 cfm/ft², the value <0.02 L/s*m² = <0.00393 cfm/ft²

Additional Testing, Compliance, and Certifications:

- ASTM E84 Class I Fire Performance
- ASTM C1029 – Type II Compliant
- ICC-1100 Standard for Spray-Applied Polyurethane Foam Plastic
- ICC Evaluation Service Report ICC-ESR-2642
- ICC-ES AC377 Appendix X-Approved for Attics & Crawl Spaces with and without prescriptive ignition barriers
- INTERTEK Code Compliance Research Report CCRR-0374
- UL 263 Fire-Resistance Rated assemblies available
- NFPA 285 commercial wall assembly fire performance, including within DuPont™ Thermax™ Wall assemblies
- NFPA 286 assemblies, multiple thermal barrier options (i.e. steel sheets)
- Florida Building Code (FBC) Approval FL47002 (per TAS 202, TAS 203 and ASTM E330)
- Miami-Dade County Notice of Acceptance- Wind Uplift Approval (NOA: 25-0605.03)
- GREENGUARD and GREENGUARD Gold Certification for VOC emissions
- ASTM C1338 – Mold resistant “Pass” rating (no growth)
- ASTM D6866 – Bio-Based content 2%

Please contact your local sales or technical representative if you have specific questions about additional WALLTITE Max properties, approvals, or certifications.

Product Overview:

WALLTITE Max is a spray polyurethane foam (SPF) system intended for installation by qualified contractors trained in the processing and application of SPF systems, as well as the plural-component polyurethane dispensing equipment required to do so. Contractors and applicators must comply with all applicable and appropriate storage, handling, processing and safety guidelines. BASF technical service personnel should be consulted in all cases where application conditions are questionable.

For high-lift and back to back applications of 2.5” to 4”, WALLTITE Max has an estimated theoretical yield range of 5,200-6,000 board feet per set. For applications less than 3” per pass, coverage may be in the range of 4500-5300 board feet per set. Actual coverage can be in excess of or below the referenced estimated theoretical range based on factors affecting density including, however, not limited to: multiple lifts, substrate texture, substrate temperature, overspray loss, windy conditions, altitude, container residue, equipment characteristics & temperatures, applicator technique, etc. For help estimating yield for this and other spray foams, please consult Spray Polyurethane Foam Alliance’s SPFA-121 SPF Estimating Reference Guide.

Installation recommendations and precautions:

WALLTITE Max is designed for an application rate of a ½” minimum to a 4” maximum, with optimized coverage in high lift applications at 3” to 4” inches thick. Installation in multiple, thinner passes could lead to increased density and reduced yield. Dual lifts can be applied back-to-back with no dwell time between passes up to a maximum of 3.5” per lift for a total of 7” in two lifts. When installed in thicknesses in excess of 3.5”, allow for 10 minutes cooling time per inch between passes. Once installed material has cooled it is possible to add additional applications in order to increase the overall installed thickness of SPF. Be aware that applications not following these recommendations may develop high exothermic temperatures. Care should be taken to allow cooling of thick passes, and to avoid excess application thickness.

WALLTITE Max is designed for installation to most standard construction materials such as wood, wood-based products, plastics, metal and concrete. Using cold weather application techniques such as flash passes and/or picture framing to wet the studs (each with 5-minute cooling time), WALLTITE Max has performed successfully onto wood substrates down to 20°F. For heat sink-materials such as metal or concrete, WALLTITE Max can be sprayed onto substrates down to 30°F, using a flash pass method. **The maximum operating temperature for BASF spray foam chemistries is 180°F.**



BASF recommends the use of mockups or sample spray before starting the full-scale project. This will provide an opportunity to see how all materials are installed and evaluate their properties prior to proceeding. Supplemental heat and wetting the studs may be required to avoid thermal shock.

See BASF WALLTITE Series HFO Insulation Guidelines for additional information or consult a BASF Representative for further information about applications using our liquid compounds.

WALLTITE Max is NOT designed for use as an EXTERIOR roofing system. BASF offers a separate line of products for exterior roofing applications. Cold-storage structures such as coolers and freezers demand special design considerations with regard to thermal insulation and moisture-vapor drive. WALLTITE Max should NOT be installed in these types of constructions, unless the structure was designed by a design professional for specific use as cold storage. For more information please contact your sales or technical representative.

Foam plastic materials installed in walls or ceilings may present a fire hazard unless protected by an approved, fire-resistant thermal barrier with a finish rating of not less than 15 minutes as required by building codes. Rim joists/header areas, in accordance with the IRC and IBC, may not require additional protection. Foam plastic must also be protected against ignition by code prescribed or properly tested materials in attics and crawl spaces. See relevant Building Codes and <http://www.iccsafe.org> for more information.

Important Material Preparation Note: Product should be stored at 50-80°F. Materials should be prepared for processing by being warmed to 70°F minimum at least 24 hours prior to installation and maintained at 70-75°F during the install process.

EQUIPMENT PROCESSING PARAMETERS:

Conditions	Side A, Side B, Hose Temperature (Adjust in ± 3°F increments)	Proportioner set Pressure (Spray pressure)
Cold	115 – 130 °F	1150 – 1450 psi (900 – 1200 psi)
Warmer	110 – 125 °F	1150 – 1450 psi (900 – 1200 psi)

Caution - Failure to follow the application precautions, safety data sheet (SDS) information as well as accepted industry practices (www.spraypolyurethane.org) may result in unwanted foam physical properties and applications that may not provide the desired results. This also includes unwanted health risks such as possible respiratory issues, sensitization or eye irritations for applicators and workers located in the area being sprayed. A full understanding of the foam processing and all safety risks must be completed before spraying.

In addition to reading and understanding the SDS, all contractors and applicators must use appropriate respiratory, skin and eye Personal Protective Equipment (PPE) when handling and processing polyurethane chemical systems. Personnel should review related industry and best practice documents published by organizations such as Spray Polyurethane Foam Alliance ([SPFA](http://www.spfa.org)), [OSHA](http://www.osha-slc.gov), Spray Foam Coalition ([SFC](http://www.sprayfoamcoalition.org)) and complete the American Chemistry Council’s online Spray Polyurethane Foam Chemical Health & Safety Training course at www.spraypolyurethane foam.org/training.

Also the following document is available from the Center for the Polyurethanes Industries (CPI): *Model Respiratory Protection Program for Compliance with the Occupational Safety and Health Administration’s Respiratory Protection Program Standard 29 C.F.R. §1910.134*

As with all SPF systems, improper application techniques should be avoided. Examples of improper application techniques include, but are not limited to excessive thickness of SPF, off-ratio material and spraying into or under rising SPF. Potential results of improperly installed SPF include dangerously high reaction temperatures that may result in fire and offensive odors that may or may not dissipate. Improperly installed SPF must be removed and replaced with properly installed

materials. LARGE MASSES of SPF should be removed to an outside safe area, cut into smaller pieces and allowed to cool before discarding into an appropriate trash receptacle.

Odor level of spray polyurethane foam is dependent on proper application using the recommended processing parameters and proper ventilation.

All areas that are sprayed incorrectly or result in A only material, B only material, improperly mixed or off ratio materials, or excessively thick applications, are to be removed and replaced with properly processed spray foam. All cleaning solvents and others materials are to be captured and properly disposed of and not left at the job site.

SPF insulation is combustible. High-intensity heat sources such as welding or cutting torches must not be used in contact with or in close proximity to WALLTITE Max or any polyurethane foam. The insulation must not be used in areas that have a maximum service temperature greater than 180°F(82°C).

SHELF LIFE AND STORAGE CONDITIONS:

WALLTITE Max has a shelf life of approximately six (6) months from the date of manufacture when stored in original, unopened containers at 50-80°F. As with all industrial chemicals this material should be stored in a covered, secure location and never in direct sunlight. Storage temperatures above the recommended range will shorten shelf life. Storage temperatures above the recommended range may also result in elevated headspace pressure within packages.

LIMITED WARRANTY INFORMATION - PLEASE READ CAREFULLY:

The information herein is to assist customers in determining whether our products are suitable for their applications. Our products are only intended for sale to industrial and commercial customers. Customer assumes full responsibility for quality control, testing and determination of suitability of products for its intended application or use. We warrant that our products will meet our written liquid component specifications. We make no other warranty of any kind, either express or implied, by fact or law, including any warranty of merchantability or fitness for a particular purpose. Our total liability and customers' exclusive remedy for all proven claims is replacement of nonconforming product and in no event shall we be liable for any other damages.

TECHNICAL ASSISTANCE

For more detailed information, contact Inside Technical Support at:

Toll-Free: 1-800-706-0712, Option 2

Email: spf.techsales@basf.com

Website: <https://spf.basf.com/>

[Technical Document Resource Center](#)

BASF Corporation | 1703 Crosspoint Avenue, Houston, TX 77054, United States

TDS-CCF-213-WT-Max

WALLTITE® is a registered trademark of BASF Corporation.

While descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/use, BASF recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use. No warranties of any kind, either expressed or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth, or that the products, designs, data or information may be used without infringing the intellectual property rights of others. In no case shall the descriptions, information, data or designs provided be considered a part of BASF's terms and conditions of sale. Further the descriptions, designs, data, and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the description, designs, data or information given or results obtained, all such being given and accepted at the reader's risk.