

WALLTITE® One Series BUILDING ENVELOPE INSULATION

[Intertek CCRR-0374](#)



DESCRIPTION:

WALLTITE One is a two-component closed-cell spray polyurethane foam system utilizing an EPA-approved, zero ozone-depleting hydrofluorolefin (HFO) blowing agent having extremely low (less than 1) global warming potential (low-GWP). It is designed for use in residential construction and common commercial insulation applications. **WALLTITE One** is compatible with most common construction materials and can only be processed with BASF Elastospray® 8000A isocyanate.

The benefits of **WALLTITE One** include:

- Superior thermal insulation
- Controls moisture infiltration
- Controls air infiltration
- FEMA Class 5 flood damage resistant rated material
- Non-fibrous
- Structural enhancement
- Speed of installation

REACTIVITIES AVAILABLE	AMBIENT TEMPERATURE RANGE
WALLTITE One R	35 – 120°F
WALLTITE One W	20 – 45°F

ADDITIONAL TESTING, APPROVALS & CERTIFICATIONS:

- ASTM E84 Class I Fire Performance
- ASTM C1029 – Type II Compliant
- UL 263 Fire-Resistance Rated assemblies available
- NFPA 285 commercial wall assembly fire performance credentials, including within DuPont™ Thermax™ Wall assemblies
- INTERTEK Code Compliance Research Report CCRR-0374
- ICC-ES AC308 Appendix X- Approved for Attics & Crawl Spaces Installations with and without prescriptive ignition barriers
- GREENGUARD and GREENGUARD Gold Certification for VOC emissions
- ASTM C1338 –Mold resistant “Pass” rating (no growth)
- ICC-1100 Standard for Spray-Applied Polyurethane Foam Plastic

Please contact your local Sales or Technical Representative for specific questions regarding additional **WALLTITE One** properties, approvals, or certifications.

PHYSICAL PROPERTIES ⁽¹⁾

PROPERTY	METHOD	WALLTITE ONE
Resin:		
Specific Gravity @ 70°F	ASTM D1638	1.2
Viscosity @ 77°F (cps)	Brookfield	500 – 700
Cured Foam:		
Density, core @ 2"-3" lifts (pcf)	ASTM D1622	2.0-2.3 nominal
Closed Cell Content (%)	ASTM D6226	>90
Thermal Resistance ⁽²⁾ (aged)		
R-value (ft ² hr °F/Btu in)	ASTM C518	7.5/ in @ < 3.5" thickness
R-value (ft ² hr °F/Btu in)		7.2/ in @ ≥3.5" thickness
Compressive Strength (psi) ⁽³⁾	ASTM D1621	>25
Tensile Strength (psi) ⁽³⁾	ASTM D1623	>32
Thermal and Humid Aging	ASTM D2126	
158°F / 97% RH / 168 hrs	(% change)	-7.6%
Water Vapor Transmission		
Permeance	ASTM E96 (Calculated)	1.32 Perms <1.0 Perms @ 1.5" (Class II vapor retarder)
Air Leakage ⁽⁴⁾	ASTM E2178	Meets <0.02 @ 0.5 inch (Air impermeable insulation)
(L/s*m ² @ 75 Pa ΔP)		
Water Absorption (vol %)	ASTM D2842	≤ 5
Surface Burning Characteristics		
Flame Spread Index	ASTM E84	≤ 25
Smoke Developed Index	ASTM E84	≤ 450

(1) These physical property values and data are typical for SPF material as applied at a development facility and from samples prepared using equipment configurations pertinent to controlled lab conditions. SPF performance and actual physical properties may vary with differences in application (i.e., ambient conditions, process equipment and settings, material throughput, etc.). As a result, these published properties should be used as guidelines solely for the purpose of evaluation.

(2) The physical property chart shows the R-value of this spray foam insulation. "R" refers to resistance to heat flow. The higher the R-value, the greater the insulating power. Refer to Installation Card and fact sheet on R-values.

(3) Minimums reported, as needed to meet ASTM 1029 Type II standards.

(4) Using a conversion factor of 1 L/s m² = 0.196850394 cfm/ft², the value <0.02 L/s*m² = <0.00393 cfm/ft²*

WALLTITE® ONE SERIES BUILDING ENVELOPE INSULATION

GENERAL INFORMATION:

WALLTITE One is a spray polyurethane foam (SPF) system intended for installation by qualified contractors trained in the processing and application of SPF systems, as well as the plural-component polyurethane dispensing equipment required to do so. Contractors and applicators must comply with all applicable and appropriate storage, handling, processing and safety guidelines. BASF technical service personnel should be consulted in all cases where application conditions are questionable.

For high-lift and back-to-back applications of up to 3.5", WALLTITE One has an estimated theoretical yield range of 5,000-5,500 board feet per set. For applications less than 2.5" per pass, coverage may be in the range of 4,500-5,000 board feet per set. Actual coverage can be in excess of or below the referenced estimated theoretical range based on factors affecting density including, however, not limited to: multiple lifts, substrate texture, substrate temperature, overspray loss, windy conditions, altitude, container residue, equipment characteristics & temperatures, applicator technique, etc. For help estimating yield for this and other spray foams, please consult Spray Polyurethane Foam Alliance's SPFA-121 SPF Estimating Reference Guide.

INSTALLATION RECOMMENDATIONS AND CAUTIONS:

WALLTITE One is designed for an application rate of a 1/2" minimum to a 3.5" maximum, with optimized coverage in high lift applications at 3 – 3.5" inches thick. Installation in multiple, thinner passes could lead to increased density and reduced yield. Dual lifts can be applied back-to-back with no dwell time between passes up to a maximum of 3.5" per lift for a total of 7" in two lifts. For installations over 7" or more than two passes, allow cooling time of 10 minutes per inch. Be aware that applications not following these recommendations may develop high exothermic temperatures, therefore avoid extreme application thickness beyond these limits.

WALLTITE One is designed for installation to most standard construction materials such as wood, wood-based products, plastics, metal and concrete. WALLTITE One has performed successfully when sprayed onto wood substrates down to 20°F when using cold weather application techniques such as flash passes and/or picture framing to wet the studs. For heat sink-materials such as metal or concrete, WALLTITE One can be sprayed onto substrates down to 30°F, using a flash pass method. Supplemental heat and wetting the studs may be required to avoid thermal shock with severe cold conditions or substrates. BASF recommends the use of mockups or sample spray before starting the full-scale project. This will provide an opportunity to see how all materials are installed and evaluate their properties prior to proceeding. See BASF WALLTITE Series HFO Application Guidelines for additional information or consult a BASF Representative for further information about applications using our liquid compounds.

WALLTITE One is NOT designed for use as an EXTERIOR roofing system. BASF offers a separate line of products for exterior roofing applications. Cold-storage structures such as coolers and freezers demand special design considerations with regard to thermal insulation and moisture-vapor drive. WALLTITE One should NOT be installed in these types of constructions, unless the structure was designed by a design professional for specific use as cold storage. For more information, please contact your sales or technical representative.

Foam plastic materials installed in walls or ceilings may present a fire hazard unless protected by an approved, fire-resistant thermal barrier with a finish rating of not less than 15 minutes as required by building codes. Rim joists/header areas, in accordance with the IRC and IBC, may not require additional protection. Foam plastic must also be protected against ignition by code prescribed or properly tested materials in attics and crawl spaces. See relevant Building Codes and www.iccsafe.org for more information.

Conditions	A side, B side, Hose Temp (Adjust in ± 3° increments)	Proportioner set pressure (Spraying pressure)
Colder	115 – 130°F	1150 – 1450 psi (900 – 1200 psi)
Warmer	110 – 125°F	1150 – 1450 psi (900 – 1200 psi)

Caution - Failure to follow the application precautions, safety data sheet (SDS) information as well as accepted industry practices (www.spraypolyurethane.org) may result in unwanted foam physical properties and applications that may not provide the desired results. This also includes unwanted health risks such as possible respiratory issues, sensitization or eye irritations for applicators and workers located in the area being sprayed. A full understanding of the foam processing and all safety risks must be completed before spraying.

In addition to reading and understanding the SDS, all contractors and applicators must use appropriate respiratory, skin and eye Personal Protective Equipment (PPE) when handling and processing polyurethane chemical systems. Personnel should review related industry and best practice documents published by organizations such as Spray Polyurethane Foam Alliance (SPFA), OSHA, Spray Foam Coalition (SFC) and complete the American Chemistry Council's online Spray Polyurethane Foam Chemical Health & Safety Training course at www.spraypolyurethane.org/training.

Also the following document is available from the Center for the Polyurethanes Industries (CPI): *Model Respiratory Protection Program for Compliance with the Occupational Safety and Health Administration's Respiratory Protection Program Standard 29 C.F.R. §1910.134*

As with all SPF systems, improper application techniques should be avoided. Examples of improper application techniques include, but are not limited to excessive thickness of SPF, off-ratio material and spraying into or under rising SPF. Potential results of improperly installed SPF include dangerously high reaction temperatures that may result in fire and offensive odors that may or may not dissipate. Improperly installed SPF must be removed and replaced with properly installed materials. LARGE MASSES of SPF should be removed to an outside safe area, cut into smaller pieces and allowed to cool before discarding into an appropriate trash receptacle.

Odor level of spray polyurethane foam is dependent on proper application using the recommended processing parameters and proper ventilation.

All areas that are sprayed incorrectly or result in A only material, B only material, improperly mixed or off ratio materials, or excessively thick applications, are to be removed and replaced with properly processed spray foam. All cleaning solvents and other materials are to be captured and properly disposed of and not left at the job site.

SPF insulation is combustible. High-intensity heat sources such as welding or cutting torches must not be used in contact with or in close proximity to WALLTITE One or any polyurethane foam. The insulation must not be used in areas that have a minimum service temperature greater than 180°F(82°C).

SHELF LIFE AND STORAGE CONDITIONS:

WALLTITE One has a shelf life of approximately six (6) months from the date of manufacture when stored in original, unopened containers at 50-80°F. As with all industrial chemicals this material should be stored in a covered, secure location and never in direct sunlight. Storage temperatures above the recommended range will shorten shelf life. Storage temperatures above the recommended range may also result in elevated headspace pressure within packages.

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY:

The information herein is to assist customers in determining whether our products are suitable for their applications. Our products are only intended for sale to industrial and commercial customers. Customer assumes full responsibility for quality control, testing and determination of suitability of products for its intended application or use. We warrant that our products will meet our written liquid component specifications. We make no other warranty of any kind, either express or implied, by fact or law, including any warranty of merchantability or fitness for a particular purpose. Our total liability and customers' exclusive remedy for all proven claims is replacement of nonconforming product and in no event shall we be liable for any other damages.

While descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/use, BASF recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use. No warranties of any kind, either expressed or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth, or that the products, designs, data or information may be sued without infringing the intellectual property rights of others. In no case shall the descriptions, information, data or designs provided be considered a part of BASF's terms and conditions of sale. Further the descriptions, designs, data, and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the description, designs, data or information given or results obtained, all such being given and accepted at the reader's risk.

Warning Polyurethanes are organic materials and must be considered combustible.